

Ardrox® 970P25E

Water Washable Fluorescent Penetrant

Type I (fluorescent), Method A (water washable) and Method C (solvent removable) AMS 2644 approved inspection penetrant.

PRIMARY APPLICATION

Ardrox® 970P25E has been approved for sensitivity Level 3.

This penetrant is characterized by its controlled washability, which makes it less susceptible to over-washing. This high entrapment feature truly makes it unique in comparison to other water washable products. Flaw finding is enhanced by its excellent bleed back properties. This product was developed for fracture critical control inspection.

Ardrox® 970P25E has a flash point of well over 300°F (149°C). Very low in odor, it contains no petroleum solvents, no heavy metals, and no fats, oils or greases as constituents. There is no loss of sensitivity due to evaporation nor will this product break down under high temperature conditions.

It provides:

- Bright, crisp indications
- Low residual background
- Exceptionally high and UV fade resistance
- Over-wash resistance
- Low toxicity

CHEMICAL CHARACTERISTICS

flash point.....	350°F (177°C), PMCC
appearance	greenish-yellow
sulfur content.....	100 ppm
chloride content.....	100 ppm
fluorides.....	25 ppm
sodium content.....	60 ppm
density	7.8 to 8.2 lb/gal
viscosity.....	22.0 to 30.0 centistokes, per ASTM D445

APPROVALS

In addition to being approved to AMS 2644, Ardrox® 970P25E is approved by all major aerospace engine and airframe manufacturers including General Electric, Rolls Royce, McDonnell Douglas, Boeing, Pratt & Whitney and Rockwell (fracture control inspection for B-1 aircraft applications.) For the nuclear industry, these products are designed to conform to the requirements of the ASME Boiler and Pressure Vessel Code (Section V, Article 6) and AECL. Chemetall Oakite manufacturing facilities are QS-9000 and

ISO 9001 certified.

APPLICATION PROCEDURE

Ardrox® 970P25E may be applied by aerosol, brushing, tank immersion, conventional and electrostatic spraying. The following typical process sequence illustrates the recommended method of use.

1. PRECLEAN/DRY

All surface contamination (rust, paint residues, greases, scale, etc.) must be completely removed. After cleaning, make sure that the component is completely dry and cool, 125°F (53°C) or lower, before applying the penetrant.

2. PENETRANT APPLICATION

Apply penetrant to the surface and leave on for a suitable dwell period. This dwell period is normally 5 minutes minimum. If the contact period exceeds 120 minutes, the penetrant should be reapplied to the surface.

3. WATER WASH – 25 to 40 psi, 1 to 3 minutes, 50° to 100°F (10° to 38°C)

Use either one or a combination of manual spray or automatic spray tank rinses.

The times given are a guide only. Practical trials should be carried out to establish the most suitable conditions for specific components.

4. OVEN DRY, AIR RECIRCULATING – Oven set at 160°F (71°C) Maximum

Use the minimum time necessary to thoroughly dry the components. Use clean, filtered, low-pressure compressed air to remove pockets of water before oven drying.

5. APPLY DEVELOPER

Dry powder developer, **Ardrox® 9D4A or D1**, may be applied in specially designed dust storm cabinets or by electrostatic spray; dwell time: 2 to 5 minutes. Non-aqueous developers, **Ardrox® 9D1B or NQ1**, are applied by spray; dwell time: dry, plus 2 minutes. The aqueous developer **Ardrox® 9D76** is applied prior to Step 4, oven dry. In most cases developers are required by government or prime contractor specifications.

6. INSPECTION

Component should be inspected under UVA (365-nm) illumination in a darkened area.

EFFECTS ON MATERIALS

Ardrox® 970P25E is non-corrosive to most common metals. It meets the corrosion requirements of AMS 2644 for aluminum, steel and magnesium. It is compatible with titanium and nickel alloys. It may stain or soften some plastics and rubbers; where appropriate, a compatibility test is recommended.

NOTES ON USE

It is recommended that tanks, in the process line, be constructed from stainless steel (Grade 304 or equivalent). For areas, which are exposed to water, mild steel may be used provided it is free from rust, scale and other contaminants.

SAFETY AND HANDLING

Prior to handling and use of any of the materials referenced in this document, the Material Safety Data Sheets should be read and understood by all personnel in contact with these materials.

KEEP OUT OF REACH OF CHILDREN

STORAGE

Dry, indoor storage at temperatures between 40°F and 100°F is recommended, away from any incompatible materials referenced in Material Safety Data Sheets. All containers should be tightly closed when not in use.

SHELF LIFE

The shelf life of **Ardrox® 970P25E** is 3 years (2 years for aerosols).

DISPOSAL

Any disposal of the materials referenced in this document should be in accordance with all applicable federal, state, and local regulations.

The process solution can contain components other than those present in the materials as supplied. Analysis of process solutions may be required prior to disposal.

Oakite Products, Inc. ("Oakite") warrants that the product or products described herein will conform with its published specifications. The products supplied by Oakite and information related to them are intended for use by buyers having necessary industrial skill and knowledge. Buyers should undertake sufficient verification and testing to determine the suitability of the Oakite materials for their own particular purpose. Since buyer's conditions of use of products are beyond Oakite's control, Oakite does not warrant any recommendations and information for the use of such products. OAKITE DISCLAIMS ALL OTHER WARRANTIES INCLUDING THE IMPLIED WARRANTY OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH THE USE OF ITS PRODUCTS.

Chemetall
Oakite



Oakite Products, Inc. P.O. Box 602, 50 Valley Road, Berkeley Heights, NJ 07922 • **Oakite Canada Limited** 115 East Drive, Bramalea, Ontario L6T1B7
Tel. (800) 526-4473 (908) 464-6900 FAX (908) 464-4658 Web site: www.oakite.com E-Mail: oakite.products@chemetall.com
Distributors and Licensees Worldwide